


Thread Size	A Head Diameter		B Unthreaded Length	Minimum	Hole in Sheet	Distance to Center of Hole in Panel	Push-Out (lbs.)	Torque-Out (InIbs.)	Estimate of Installation Force in Steel  Tons (Approx)
	2-56	.156	.125	.075	.040	.085	.18	250	
4-40	.204	.172	.085	.040	.111	.22	280	11	4
6-32	.219	.187	.090	.040	.137	.25	350	30	4.5
8-32	.250	.218	.090	.040	.163	.28	400	65	5
10-24	.266	.234	.100	.040	.189	.28	500	100	6
10-32	.266	.234	.100	.040	.189	.28	500	100	6
1/4-20	.344	.312	.135	.062	.249	.31	700	120	7
5/16-18	.391	.361	.160	.093	.311	.38	850	200	8
3/8-16	.467	.435	.185	.125	.374	.45	1000	260	5.5
1/2-13	.640	.630	.170		.502	.62			

Description	A fastener with unified thread pitch and a cylindrical, low profile head with small, rectangular ribs protruding from the underside of head. The top of the head is flat and is flush with the mating surface when installation is complete. Below the ribs and above the thread is an annular groove which helps to hold the fastener in position.					
Applications/ Advantages	Intended for metal panel-to-panel applications and well-suited for use in printed circuit boards. A hole is pierced into the circuit board and the unit it is attached to. The stud is inserted using a hand press or by hand, applying parallel squeezing forces. A hex nut is twisted onto the stud, securing it from the back. As the nut is tightened, the ribbed stud head grips the front panel to secure the application from the front as well, eliminating the need for welding. As the application force is applied, part of the sheet cold flows into an undercut under the head, making the fastener an integral part of the sheet.					
Material	Steel	Stainless				
Material	Low carbon steel	300 series stainless				
Heat Treatment	Clinch studs shall be case hardened, oil quenched and tempered.	-				
Case Hardness	Rockwell C 45 minimum	Not required to test for hardness				
Core Hardness	Rockwell C 29 - 38	Not required to test for hardness				
For Use In	materials with a hardness of Rockwell B80 or less.	materials with a hardness of Rockwell B70 or less.				
Finish	Steel clinch studs are usually furnished with a zinc plating.	Stainless clinch studs are commercially passivated.				


### Flush Head

### 12-Rib Style

## Self-Clinch Studs



## By D




#### THIN SHEET ANVIL

Intended for panels less than 0.060" in thickness, with #4 thru #10 thread sizes, inclusive. Also, for panels less than 0.093" in thickness with 1/4" thread size.

#### THICK SHEET ANVIL

Intended for panels 0.060" and greater in thickness, with #4 thru #10 thread sizes, inclusive. Also, for panels 0.093" and greater in thickness with 1/4" thread size.

# PRESS



Anvil Dimensions							
Thread Size	Anvil						
Tilleau Size	В	T					
2-56	0.110	0.087					
2 00	0.114	0.090					
4-40	0.136	0.113					
4-40	0.140	0.116					
6-32	0.162	0.139					
0-32	0.166	0.142					
8-32	0.188	0.165					
0-32	0.192	0.168					
10-24 & 10-32	0.216	0.191					
10-24 & 10-32	0.220	0.194					
1/4-20	0.295	0.250					
1/4-20	0.300	0.253					
5/16-18	_	0.3125					
5/10-18	_	0.3155					
3/8-16	_						
3/0-10	_						

**Notes on Installation:** Apply only sufficient squeezing pressure to embed head of stud flush with panel. Do not use more pressure than necessary. Amount of pressure varies with panel material and size of stud. Studs install flush in sheets .040" or thicker but will project up to .020" in thinner sheets.

## Fasteners By Design Inc.